

Technical Data & Specification

Asphalt: Loose Mix

Indicator	Test Value	Method
Rice's RD	2.594	TMH1 C4/86
Bitumen Content (%)	6.1	TMH1C7 (b)/86

Grading

Sieve Size (mm)	Cum. Percentage passing (%)	Method
13.2	100	TMH1 B4/86
9.5	100	
6.7	91	
4.75	48	
2.36	17	
1.18	14	
0.60	9	
0.30	7	
0.15	6	
0.075	4.8	

Asphalt: Briquettes

Indicator	Test Value	Method
Marshall Stability (kN)	5.3	TMH1 C2/86
Marshall Flow (mm)	2.6	TMH1 C2/86
Bulk Relative Density	2.432	TMH1 C3/86
Air Void Content (%)	5.4	TMH1 C2 & C3/86

Deviation from test method:	Deviation from test method: After compaction the briquettes were left to cure for 8 weeks
-----------------------------	---

repair[®] standard grade aggregate grading

